20

25

5

What is claimed is:

1. A filter cartridge which is prepared by winding a non-woven fabric strip comprising a thermoplastic fiber around a perforated cylinder in a twill form, wherein the non-woven fabric strip satisfies the following equation (A):

 \log_{10} Y < 3.75 - 0.6 (\log_{10} X) (A) wherein X (cm³/cm²/sec) is an airflow amount of the non-woven fabric strip measured in accordance with JIS L 1096-A

(1990), and Y (g/m^2) is a basis weight thereof.

2. A filter cartridge which is prepared by winding a long fiber non-woven fabric strip comprising a thermoplastic fiber around a perforated cylinder in a twill form, wherein the non-woven fabric strip satisfies the following equation (B):

 $\log_{10} Y < 3.75 - 0.75 (\log_{10} X)$ (B) wherein X (cm³/cm²/sec) is an airflow amount of the non-woven fabric strip measured in accordance with JIS L 1096-A (1990), and Y (g/m²) is a basis weight thereof.

- A filter cartridge which is prepared by winding a non-woven fabric strip comprising a thermoplastic fiber around a perforated cylinder in a twill form, wherein in winding in a twill form, a number (W) of winding the non-woven fabric strip from one end to the other end in a longitudinal direction of the perforated cylinder is one to 10 per a length of 250 mm in the perforated cylinder.
- 4. The filter cartridge as claimed in claim 3, wherein when a 2-fold value (2W) of the winding number (W)

figures or less which is a non-reducible approximate value, the denominator is 4 to 40.

The filter fartridge as claimed in any one of

The filter cartridge as claimed in any one of elaims 1 to 3, wherein at least a part of fiber intersections of the non-woven fabric strip is thermally bonded.

is represented by a fraction having a denominator of two

- 6. The filter cartridge as claimed in any one of claims 1 to 3, wherein the non-woven fabric strip has a width of 0.5 to 40 cm.
- 7. The filter cartridge as claimed in any one of claims 1 to 3, wherein a product of a width (cm) and a basis weight (g/m^2) of the non-woven fabric strip is 10 to 200.
- 8. The filter cartridge as claimed in any one of claims 1 to 3, wherein the non-woven fabric strip has a thickness of 0.02 to 1.20 mm.
- 9. The filter cartridge as claimed in any one of claims 1 to 3, wherein the non-woven fabric strip is thermal compression bonded by means of a heat embossing roll having an embossing area rate of 5 to 25%.

The filter cartridge as claimed in any one of claims 1 to 3 wherein the filter material of the filter cartridge has a void rate of 65 to 85%.

11. The filter cartridge as claimed in claim 1 or 3, wherein the non-woven fabric strip is of a long fiber non-woven fabric.

20\

25

5

- 12. The filter cartridge as claimed in claim 11, wherein the long fiber non-woven fabric is produced by a spun bonding method.
- The filter cartridge as claimed in claim 1 or 3, 13. wherein the non-woven fabric strip is of a melt blown nonwoven fabric.
- The filter cartridge as claimed in any one of 14. claims 1 to 3, wherein the thermoplastic fiber is a composite fiber/comprising a low melting resin and a high melting resin/a difference of the melting points between these resins/being 10°C or more.
- The filter cartridge as claimed in any one of 15. claims 1 to 3, wherein the thermoplastic fiber is a fiber formed ffrom at least one thermoplastic resin selected from the group consisting of a polyester resin, a polyamide resin, a polyethylene resin and a polypropylene resin.
- A process for producing a filter cartridge, which 16. comprises winding a non-woven fabric strip comprising a thermoplastic fiber around a perforated cylinder in a twill form, wherein the non-woven fabric strip satisfies the following equation (A):

 $\log_{10} Y < 3.75 - 0.6 (\log_{10} X)$ (A) wherein X (cm³/cm²/sec) is an airflow amount of the nonwoven fabric strip measured in accordance with JIS L 1096-A (1990), and Y (g/m^2) , and Y (g/m^2) is a basis weight thereof.

20

25

5

17. A process for producing a filter cartridge, which comprises winding a non-woven fabric strip comprising a thermoplastic fiber around a perforated cylinder in a twill form, wherein in winding in a twill form, a number (W) of winding the non-woven fabric strip from one end to the other end in a longitudinal direction of the perforated cylinder is one to 10 per a length of 250 mm in the perforated cylinder.